Model BB8DH

270AH 12V

LiFePO4 Deep Cycle Battery

Data sheet

Electrical Specification

Voltage	12V
Capacity	270AH
Operating Temperature	- 4°F to 135°F (-20°C to 57.2°C)
Efficiency	99%
Self Discharge	2-3% per month
Maximum Series Voltage	48V
Cycles	3K-5K
Built-in BMS	Internal
Resistance	5 mΩ
Usable DoD	100%

Discharging Specification

Max Discharge Current	300A
Peak Discharge Current	500A for 30 Seconds
Surge for Loads over 500A	.5 Seconds
Recommended LVD	10.5V
BMS Discharge Voltage Cut-Off	10V
Reconnect Voltage	10V
Short Circuit Protection	Yes

Recognized Specification

Certifications	UN38.3, ULCSA-62133-2
Shipping Class	UN3480, Class 9

Drawing Specification



Charging Specification

Recommended Charge Current	.5c
Max Charge Current	135A
Absorption Voltage	14.2V-14.6V
Float Voltage	13.2V-13.8V
Equalization Voltage (if applicable)	14.4V
Absorption Time	60-90 Minutes per 270AH battery bank
BMS Charge Current Cut-Off	.5C Recommended
Recharge/Rebulk Voltage	13.3V
BMS Cell Balancing Voltage Range	14.2V-14.6V
High BMS Voltage Protection	14.7VDC
Temperature Compensation	No

Mechanical Specification

Dimensions	21.29"L X1 1.59"W X 10.01"H
Weight	81.4 lbs.
Terminal Type	.25" Brass
Terminal Hole	3/8" hole and 3/8" or 5/16" hardware is suggested
Terminal Torque	9-11 Ft-lb.
Case Material	ABS Fire Rated
Cell Type - Electrolyte	LiFeP04
Sealed and Water Resistant Case	Non-Submersible
Heat enable Terminal	Female M4 Thread

Temperature Specification

Discharge Temperature	-4°F to 135°F (-20°C to 57.2°C)
Charge Temperature	25°F -135°F
Storage Temperature	-10°F to 140°F (-23°C to 60°C)
BMS High Temperature Cut-Off	>135°F
BMS Reconnect Temperature	<135°F

Model BB8DH

270AH 12V

LiFePO4 Deep Cycle Battery

Data sheet

Performed Operation Data

.5C Discharge with Temperature Variations



1C Discharge Voltage with Temperature Variations



.5C State of Charge with Temperature Variations



Standard Charge Curve with 3 Stage Charger



8DH Heater Draw Expected in a 24Hr Period





	ON	OFF	Total Cycle Time	Ah One Cycle	Ah Expected (24 Hr Period)
15F	7.6	3.73	11.33	30.39	64.35
20F	5.66	4.45	10.11	22.63	53.73
25F	4.55	4.91	9.46	18.2	46.17

*Note: The storage temperature range is -10°F to 140°F (-23°C to 60°C). We recommend bringing the Battle Born Batteries to a 100% charge and then disconnecting them completely for storage. After six months in storage, your batteries will remain 75 – 80% charged.

Storing batteries in subzero weather (-15°F or more) has the potential to crack the ABS plastic and more importantly could cause a faster loss of capacity, in some cases drastically more than the typical 2 – 4% per month loss.