



Measures Technology Values Innovation



## VRLA Rechargeable Battery

# HRC1234W (HRC1234WFR)

### FEATURES

- Maintenance free(no water topping-up required)
- No free acid(Non-spillable battery)
- Can be used in any orientation(excluding used inverted)
- The battery is designed for high rate usage
- Its design life is up to 5 years in floating application
- Absorbent Glass Mat technology for efficient gas recombination
- The power density at 5 min~15min discharging rate is 30% higher than BP series

### APPLICATION

- UPS
- Laboratory Equipment
- Power Packs



### SPECIFICATIONS


Nominal Voltage	12V	
Nominal Capacity	10 Hour Rate (700mA, 10.5V)	7.00 Ah
	15 Min Rate (204W, 7.8V)	4.25 Ah
Approx. Weight	2500g(5.51lbs.)	
Terminals	T2 (Faston Tab 250) T1 is optional	
Max. Discharge Current	105 A (5 sec.)	
Max. Charge Current	2.1 A	
Operating Temperature Range	Charge	0°C~40°C(32°F~104°F)
	Discharge	-20°C~50°C(-4°F~122°F)
	Storage	-20°C~40°C(-4°F~104°F)
Self Discharge	< 3% per month (25°C)	
Internal Resistance	≤20mΩ (Fully Charged )	

### CONTAINER MATERIAL

- HRC1234W:  
ABS: 94-HB (Dark gray color)
- HRC1234WFR:  
ABS: 94-V0 (Light gray color)



<b>UL</b> ISO9001	<b>UL</b> ISO14001
<b>UL</b> MH19884	<b>CE</b> C4M20310-2474-E-16
● IEC61056	● JIS C 8702
● GB/T 19639	

OUTER DIMENSIONS mm(inch)	Length (L)	Width (W)	Container Height (H)	Total Height (TH)
	151±1.5(5.94±0.06)	65±1.5(2.56±0.06)	94±1.5(3.70±0.06)	100±2.0(3.94±0.08)



**HRC1234W (HRC1234WFR) discharge characteristics (25°C/77°F)**


**Battery Charging Characteristics**



**Charging Procedure**

Application	Charging method	Charging Voltage at 25°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C/cell)	Max. charging current (CA)	Charging time 0.1CA, 25°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service					16	10	

**Effect Of Temperature On Long Term Float Life**



**Constant power discharge characteristics at 25 °C/77 °F Unit: W**

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	20 Min	30 Min	40 Min	50 Min	60 Min	120 Min
1.80V	328.0	224.0	172.3	138.4	105.2	80.0	66.8	58.8	32.4
1.70V	392.0	250.0	187.4	146.6	109.6	83.0	69.0	60.2	33.1
1.60V	420.0	263.0	195.9	152.0	112.0	85.0	70.4	61.2	33.6
1.50V	432.0	268.0	200.2	154.4	113.4	86.0	71.2	61.8	33.8
1.40V	440.0	271.6	202.5	155.8	114.2	86.6	71.8	62.2	33.9
1.30V	444.0	274.0	204.0	156.8	114.8	87.0	72.2	62.4	34.0

**Constant current discharge characteristics at 25 °C/77 °F Unit: A**

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	20 Min	30 Min	40 Min	50 Min	60 Min	120 Min
1.80V	29.29	19.65	14.92	11.87	8.92	6.73	5.59	4.90	2.70
1.70V	35.64	21.93	16.22	12.57	9.29	6.98	5.77	5.02	2.76
1.60V	38.18	23.07	16.96	13.04	9.49	7.15	5.89	5.10	2.80
1.50V	39.27	23.51	17.33	13.24	9.61	7.23	5.96	5.15	2.82
1.40V	40.00	23.82	17.53	13.36	9.68	7.28	6.01	5.18	2.83
1.30V	40.36	24.04	17.66	13.45	9.73	7.32	6.04	5.20	2.83

All data shall be changed without prior notice, BB reserves the right to explain and update the information contained hereinto.

Trial A/2 REV. Dec. 2011

**USA:**  
B&B BATTERY(USA) INC.  
6415 RANDOLPH ST.COMMERCE,CA,90040 U.S.A.  
TEL:1-323-278-1900.1-800-278-8599  
FAX:1-323-278-1268  
E-Mail:sales@bb-battery.com

**CHINA FACTORY:**  
B.B. BATTERY CO., LTD.  
CHENG DONG TRIAL AREA,HUANG GANG,  
RAOPING, GUANG DONG,CHINA,515700  
TEL:86-768-7601001-2  
FAX:86-768-7601469  
E-Mail:maggy@bb-battery.com

**EUROPE:**  
B&B BATTERY(EUROPE) B.V.  
SUITE 8, HAAKSBERGWEG 33, 1101  
BP AMSTERDAM, THE NETHERLANDS  
TEL: 31-30-3200190  
MOBILE: 886-933896989  
E-Mail: gary@bb-battery.com

**HONG KONG:**  
B&B BATTERY(Hong Kong) Co.  
TEL:852-2311-4918  
FAX:852-2739-1182  
E-Mail:bbhk@hkstar.com

**JAPAN:**  
B&B BATTERY(JAPAN) CO., LTD.  
1375-11 NARAHARA-MACHI,HACHIOJI,  
TOKYO 193-0803,JAPAN.  
TEL:81-426-25-6375  
FAX:81-426-25-6375  
E-Mail:miyata@bb-battery.com

**TAIWAN:**  
B.B. BATTERY(TAIWAN) CO., LTD.  
TEL:886-6-502-5150  
FAX:886-6-589-8087  
E-Mail:kevin@bb-battery.com