

# S4A550-144MH10



144 Half-cut Bifacial **Transparent Back Sheet** 10BB Mono Perc







# America's Solution for Quality, Performance, and Reliability.

Our products are manufactured locally in the US, under the highest quality standards.



# 10BB Half-Cut Cell Technology

Efficient circuit design, lower internal current, lower RS loss, GA doped wafer



# Significantly Lower Risk of Hot Spot Special circuit design with much lower hot spot temperature



# **Excellent Anti-PID Performance** 2X industry standard Anti-PID



## Lower LCOE 2% more power generation



**IP68 Junction Box** High waterproof level

MODULE EFFICIENCY 21.3%

# HIGH POWER OUTPUT

550W



UL61730 (Jan)



Solar4America Technology Inc. is headquartered and has module production facilities in Sacramento, California. Our S4A branded product line offers high quality, exceptional performance, and great value to our customers. Our state-of-the-art manufacturing facility uses industry-leading automated production equipment to optimize product performance and quality.

# S4A550-144MH10

144 Half-cut Cell | 10BB Mono Perc | Transparent Back Sheet

### **ELECTRICAL PARAMETERS**

Module Type	S4A	530	S4A	\$35	S4A	540	S4A	.545	S4A	.550
Testing Condition	STC	NMOT								
Maximum Power - Pmax (W)	530	395	535	398	540	402	545	406	550	410
Maximum Power Voltage - Vmpp (V)	41.32	38.6	41.48	38.7	41.64	38.8	41.80	39.0	41.96	39.1
Maximum Power Current - Impp (A)	12.83	10.24	12.90	10.30	12.97	10.36	13.04	10.41	13.11	10.47
Open Circuit Voltage - Voc (V)	49.32	46.4	49.46	46.5	49.60	46.7	49.76	46.8	49.92	47.0
Short Circuit Current - Isc (A)	13.72	11.06	13.79	11.12	13.86	11.17	13.93	11.23	14.00	11.28
Module Efficiency	20.5	50%	20.7	70%	20.9	90%	21.1	0%	21.3	30%

STC: irradiance 1,000 W/m<sup>2</sup>; Spectra at AM 1.5; module temperature 25°C. Power output tolerance: 0~+5W. Measuring tolerance of power: ±3% NMOT: irradiance 800 W/m<sup>2</sup>; Spectra at AM 1.5; Cell temperature 45°C; Ambient temperature 20°C. Wind speed 1m/s

BIFACIAL REARSIDE POWER GAIN Electrical characteristics with different rear side power gain for reference to 550W front.

Module		Bifaciality: 70±5%				
Maximum Power	Pmax Gain	Voc/V	lsc/A	Vmp/V	Imp/A	
578W	5%	49.92	14.70	41.96	13.77	
605W	10%	49.92	15.40	41.96	14.42	
633W	15%	49.92	16.10	41.96	15.08	
660W	20%	49.92	16.80	41.96	15.73	
688W	25%	49.92	17.50	41.96	16.39	

Bifacial gain: the additional gain from the rear side compared to the power of the front side at the standard test condition. It depends on mounting (structure, height, tilt angle, etc.) and albedo of the ground.

#### **TEMPERATURE CHARACTERISTICS**

NMOT	43°C (±2°C)
Temperature Coefficient of Pmax	-0.35%/°C
Temperature Coefficient of Isc	+0.048%/°C
Temperature Coefficient of Voc	-0.26%/°C

#### MATERIAL CHARACTERISTICS

Dimensions	2279×1134×35mm (L×W×H)				
Weight	28kg				
Frame	Silver anodized aluminum alloy				
Glass	3.2 mm coated tempered glass				
Cell Encapsulation	EVA (Ethylene-Vinyl-Acetate)				
Back Sheet	Transparent				
Solar Cells	144(6×24) monocrystalline (182mm×91mm)				
Junction Box	IP68, 3 bypass diodes				
Cable & Connector	Length 1400mm, 1x4mm <sup>2</sup> / MC4 and MC4 Compatible				

#### MAXIMUM RATINGS

Maximum System Voltage (V)	1500			
Series Fuse Rating (A)	25			
PACKAGING				
PACKAOINO				
Pallet Dimensions	2304x1130x1247mm			
Pallet Quantity	31 Modules			
Truck (53') Quantity	744 Modules			
SYSTEM DESIGN				
Temperature Range	-40°C to +85°C			
Mechanical Load Front	5,400 Pa			
Mechanical Load Back	2,400 Pa			
Safety Protection Class	Class II			





