

MOTIVE J185PG-AC

MODEL	J185PG-AC with Bayonet Cap
VOLTAGE	12
MATERIAL	Polypropylene
DIMENSIONS	Inches (mm)
BATTERY	Deep-Cycle Flooded/Wet Lead-Acid Battery
COLOR	Maroon
WATERING	HydroLink™ Watering System



12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	VOLTAGE	CELL(S)	TERMINAL TYPE ^G	DIMENSIONS ° INCHES (mm)			WEIGHT ^H LBS. (kg)
		185PG-AC 12 6 7	12 6	7	LENGTH	WIDTH	HEIGHT F	114 (50)
921	J100PG-AU			15.41 (391)	6.90 (175)	14.65 (372)	114 (52)	

ELECTRICAL SPECIFICATIONS

CRANKING PERFORMANCE CAPACITY * MINUTES		CAPACITY ^B AMP-HOURS (Ah)			ENERGY (kWh)	INTERNAL RESISTANCE (m Ω)	SHORT CIRCUIT CURRENT (amps)			
C.C.A. ^D @ 0°F (-18°C)	C.A. ^e @ 32°F (0°C)	@ 25 Amps	@ 75 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr		
_	—	380	104	168	189	205	226	2.71		—

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V	24V	36V	48V	
Bulk Charge	14.82	29.64	44.46	59.28	
Float Charge	13.50	27.00	40.50	54.00	
Equalize Charge	16.20	32.40	48.60	64.80	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

MADE IN THE

ADD	SUBTRACT				
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F				
OPERATIONAL DATA					

OPERATING TEMPERATURE	SELF DISCHARGE
-4°F to 113°F (-20°C to +45°C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	5 – 15% per month depending on storage temperature conditions.

RECYCLE RESPONSIBLY



STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	SPECIFIC GRAVITY	CELL	12 VOLT
100	1.277	2.122	12.73
90	1.258	2.103	12.62
80	1.238	2.083	12.50
70	1.217	2.062	12.37
60	1.195	2.040	12.24
50	1.172	2.017	12.10
40	1.148	1.993	11.96
30	1.124	1.969	11.81
20	1.098	1.943	11.66
10	1.073	1.918	11.51

TROJAN J185PG-AC PERFORMANCE

1000 **Estimation Purposes Only** 100 Discharge Current (amps) 10 1 100 10000 1000 100000 10 Time (mins)


140 60 50 120 40 100 30 80 20 Temperature (F) 60 10 40 0 20 -10 0 -20 -20 -30 -40 -40 20% 40% 60% 80% 100% 0% 120% Percent of Available Capacity


E. C.A. (Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above


CAL (claiming runps) The doctary for an important many runp value of data in the run value of the manual of the doctary for an important of the doctary of the run value of the run value

PERCENT CAPACITY VS. TEMPERATURE

BATTERY DIMENSIONS (shown with UT)







Q

Temperature

TERMINAL CONFIGURATIONS⁶

7	UT	UNIVERSAL TERMINAL
	9	Terminal Height Inches (mm) 1.10 (28) Torque Values in-Ib (Nm) 95 – 105 (11 – 12) Bolt 5/16"

The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above Α.

- В
- C. D. C.C.A. (Cold Cranking Amps) - the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.



Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

- To function of minutes in a voltage above and enter when discharged at a constant rate at our 1/27 of and maintain a voltage above 1.75 W/cell. Capacities are based on peak performance. The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 W/cell. Capacities are based on peak performance.
- Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing minimum.



© 2019 Trojan Battery Company, LLC. All rights reserved. Trojan Battery Company is not liable for damages that may result from any information provided in or omitted from this publication, under any circumstances. Trojan Battery Company reserves the right to make adjustments to this publication at any time, without notice or obligation.

F. G.

H. Weight may vary.

